

TRUE GRIT™ EXTREME

ROOFING UNDERLAYMENT

Proudly made in North America



Florida Building Code Approved FL22409
ASTM D226 TYPE II ICC-ES AC 207 ASTM E108 CLASS A
CSA A123.3 CSA A220.1 ASTM D4869

TRUE GRIT™ EXTREME is our 30# 7 mils synthetic roofing underlayment that's for jobs when only the best will do. Metal, clay roof jobs or roofs subject to extreme conditions are best suited for **TRUE GRIT™ EXTREME**. Like our other products our it features **TRUE GRIT Technology™**, a top-side coating that provides an incredibly coarse, sandpaper like grip. It provides superior traction underfoot and allows you and your team to focus on installing, while **TRUE GRIT Technology™** focuses on your safety.

Benefits

- **TRUE GRIT Technology™**
- No tears - Much stronger than 30# asphalt felt
- Light - Easier to handle and carry than felt
 - 10 Sq. TRUE GRIT EXTREME weighs 25 lb
 - 2 Sq. 30# asphalt felt weighs 42 lb
- **180 Day UV exposure**
- No asphalt - will not rot, dry-out, nor support mold growth
- No buckling, warping or cracking
- Dependable long term moisture protection for the roof
- Lays flat for quick and easy install
- Less laps - 48" wide TRUE GRIT EXTREME vs. 36" asphalt felt
- Cool green color to reduce heat absorption on install
- **Lifetime limited warranty**
- 100% Recyclable - Considered a green building product

Specifications

ROLL SIZE	10 SQUARES	4 SQUARES
Surface Covered	1000 ft ² (92.9 m ²)	400 ft ² (37.2 m ²)
Length	250 ft (76.2 m)	100 ft (30.5 m)
Width	48" (1219 mm)	48" (1219 mm)
Rolls per Pallet	56	120
Weight per Roll	25 lbs	11 lbs

PROPERTIES	TEST METHOD	TRUE GRIT™ EXTREME
Breaking Strength (lbf/in-width)	ASTM D 226	66 Longitudinal (with fiber grain)
	ASTM D 226	57 Transverse (across fiber grain)
Tear Resistance; min; (lbf)	ASTM D 4073	82 MD Longitudinal (with fiber grain)
	ASTM D 4073	79 CMD Transverse (across fiber grain)
Pliability	ASTM D 228	Pass - Longitudinal / Transverse
Behavior (loss) on Heating	ASTM D 228	- 0.0
Liquid Water Transmission [Pass/Fail]	ASTM D 4869	Pass
Dimensional Stability (%)	ASTM D 1204	2.5 Longitudinal (with fiber grain)
	ASTM D 1204	2.5 Transverse (across fiber grain)
Unrolling @ 30°F and 140°F; [Pass/Fail]	N/A	Pass
Nominal Thickness	ASTM D1777	7 mils



Atlantic Coated Papers 1605 McEwen Dr. Whitby, Ontario L1N 7L4 1-886-299-1675

atlanticcoatedpapers.com